

A1.5 Determining a Group Number for some surface finishes

.....

For the purposes of compliance with the *surface finish* requirements, the specified combinations of substrate and coating in Table A1 can be taken as having the performance indicated without the need for further evaluation using A1.2 or A1.3.

Table A1 Specified performances for some substrate and coating combinations		
Coating (coating in good condition and well adhered to substrate)	Substrate	Performance (with or without coating)
Waterborne or solvent borne paint coatings ≤ 0.4 mm thick Polymeric films ≤ 0.2 mm thick	Concrete and masonry ≥ 15 mm thick Sheet metal ≥ 0.4 mm thick, or Fibre-cement board ≥ 6.0 mm thick Glass	G1-S
Waterborne or solvent borne paint coatings ≤ 0.4 mm thick	Gypsum plasterboard with or without paper facing ≥ 9.5 mm thick ≥ 400 kg/m ³ core density < 5% wt organic contribution to board	G2-S
Waterborne or solvent borne paint coatings, varnish or stain ≤ 0.4 mm thick ≤ 100 g/m ²	Solid wood or wood product ≥ 9.0 mm thick ≥ 600 kg/m ³ for particle boards, or ≥ 400 kg/m ³ for all other wood and wood products	G3
Note: The requirements of this table do not apply to metal faced panels with polymeric substrate.		