

Resene product labels are updated from time to time. This label is provided as a guide for this product and may differ from the label on the container you purchase.

Please discuss your project with your local Resene ColorShop team or reseller to ensure you have the right products to give you the best quality finish for your specific project.

# Resene

## AquaShield

### CoolColour™

#### mineral effect finish

#### exterior

A-LL7396004 3/20

**SAFETY PRECAUTIONS**

Read label before use. Keep out of reach of children. This material is quite bland; with vapour, occasional skin contact and even minor ingestion having negligible hazard. Repeated skin contact may, and any eye contact will, cause irritation. Harmful to aquatic life.

**PRECAUTIONS**

USE WITH ADEQUATE VENTILATION. DO NOT EAT, DRINK OR SMOKE WHILE USING.

Store in original or correctly labelled container, tightly closed, in a well ventilated area indoors, away from foodstuffs, at an ambient temperature and avoid freezing conditions. Dispose of empty container safely. Consult Resene checklist on environmentally acceptable methods of cleaning equipment and disposing of unwanted paint. Avoid release to the environment.

**FIRST AID**

IF SWALLOWED: Rinse mouth. Call a POISON CENTRE, doctor or physician if you feel unwell. IF ON SKIN (or hair): Rinse skin with plenty of soap and water. If skin irritation or rash occurs get medical advice or attention.

IF IN EYES: Rinse cautiously with water for several minutes. If eye irritation persists get medical advice or attention.

IF INHALED: If breathing is difficult, remove to fresh air and keep at rest in a position comfortable for breathing.

If medical advice is required have product container or label at hand.

Further information can be obtained from  
AUST: POISONS INFORMATION CENTRE 131 126 or call Resene 1800 738 383.  
NZ: NATIONAL POISONS CENTRE 0800 POISON (764 766) or call Resene 0800 737 363.

For use as a decorative/protective coating.  
For full technical instructions see Data Sheet D601C.

**SPILLS:** Wear appropriate protective clothing. Absorb with sand or earth. Collect and seal in properly labelled drums. Do not allow to enter drains or to run off into waterways. Refer to local waste management authority.

**CLEANING PAINT EQUIPMENT:** Brush/roll out as much paint as possible onto newspaper before washing brushes and rollers. Dispose of wash-up water onto grassy/unsealed area or into inside sink/basin, NOT into outside stormwater drain where it may harm fish in local waterways.

Resene AquaShield CoolColour™ is a high mineral content super-hydrophobic, water repellent coating for application on most porous building materials to impart watershedding properties. Combines the water repellent properties of silicones with a special surface microstructure considerably reducing the contact area for water and dirt. The result: dirt particles adhere loosely and are more easily carried away by raindrops, leaving a dry and attractive facade. Ideal for highly stressed weather-exposed facades. Made to the original Deutsches Patentschrift 1284007. Resene CoolColour technology uses sophisticated pigment technology to reflect more of the sun's energy than a standard colour, reducing heat build-up and stress on the coating and substrate. Resene CoolColours perform optimally on dark colours that are the most susceptible to heat build-up.

**Preparation**

- Ensure substrates to be coated are in sound condition, dry, free from dirt, dust, loose material, oil (including mineral oil based wood finishes or similar) and salt.
- Remove accumulated windblown salt by washing with Resene Paint Prep and Housewash (see Data Sheet D812).
- Waterblasting is the best surface preparation prior to painting of weathered cementitious surfaces.
- If mould is present, treat with Resene Moss & Mould Killer (see Data Sheet D80).
- Efflorescence on masonry **must be treated** (see Data Sheet D83).
- Wherever oil and grease are present ensure the surface to be painted is thoroughly cleaned using Resene Paint Prep and Housewash. Flush clean with water.
- For heavy contamination and cleaning of GRC panels scrub down with Resene Emulsifiable Solvent Cleaner (see Data Sheet D804) then rinse clean with water.

- All loose powdery material must be removed. If waterblasting is not possible thoroughly wire brush.
- **All sanding dusts may be harmful and appropriate protection must be worn. In particular dusts from old lead or chromate based paints or old building materials containing asbestos may be injurious to**

**health if inhaled or ingested. Seek expert advice if the presence of these materials is suspected.**

- Fill cracks with a suitable elastomeric paintable sealant after priming with Resene Sureseal (see Data Sheet D42).
- This product may be used to paint a wide variety of surfaces. If the surface you propose to paint is unsound or not referred to, try a small test area first or contact your local Resene ColorShop or reseller for advice.

**Priming**

- All surfaces that are in poor condition or affected by efflorescence or which are friable, powdery or chalky must be primed with Resene Sureseal.
- Sealants - special coating requirements of construction sealants and fillers should be followed.
- Sound cementitious surfaces do not normally require a primer. Porous cementitious surfaces require treatment with Resene Waterborne Aquapel (see Data Sheet D65).

**Application**

- Apply two coats at 12.5 square metres per litre allowing at least two hours between coats.
- Colours may lighten on exposure necessitating extra care if touching up.

**Be PaintWise**

For tips on responsible disposal of paint, cleaning equipment and minimising the impact of your decorating on the environment see the Resene website. Do not discharge any paint into the environment. Resene PaintWise (NZ) or paintback.com.au (Australia) accepts residual unwanted paint and packaging. Or contact your Local Authority for disposal information.



AquaShield TDS

the paint the professionals use  
CoolColour TDS

In Australia: Resene Paints (Aust) Limited  
7 Production Ave, PO Box 924, Beenleigh, Qld 4207  
Ph 1800 738 383 Visit [www.resene.com.au](http://www.resene.com.au)

In New Zealand: Resene Paints Limited  
Vogel St, PO Box 38242, Wgtn Mail Centre, Lower Hutt 5045  
Ph (04) 577 0500 Visit [www.resene.co.nz](http://www.resene.co.nz)

Manufactured under a quality system certified as complying with ISO9001 by Telarc SA, an accredited certification body. Printed on environmentally responsible paper, which complies with the requirements of environmental management systems EMAS and ISO14001, using vegetable-based inks.

**Quick check**

**Use on:** Exterior stucco, natural stone, tilt slab, poured concrete, bricks, concrete blocks and fibrous plaster.

**Gloss level:** Flat.

**Coverage:** 12.5 square metres per litre per coat.

The spreading rate recommended for this product will achieve hiding in two coats for most colours. Increased spreading rates can be used but additional coats may be needed to achieve hiding. See the Resene website for more information.

**Dry time (minimum):** 45 minutes.

Do not apply at temperatures below 5°C or when temperatures are liable to drop below this during the drying period. Drying is slowed by low temperatures and high humidity.

**Recoat time (minimum):** 2 hours.

**Primer required:** Yes, dependent on surface.

**Usual number of coats:** Two.

**Application method:** Brush, roller or airless spray.

**Clean up:** Water.

**Colour range:** Selected Resene Total Colour System including BS5252, Multi-finish, Whites & Neutrals and The Range.

Application of a Resene CoolColour will reflect more heat than the same colour made using non-cool pigmentation and reduce heat related stress on the substrate; it will not make the painted surface cool to touch. Check with Resene staff whether a Resene CoolColour is right for your project.

**Before use:** Stir well with a wide flat stirrer.

Enjoy the Resene Promise of quality on premium paints. See your Resene ColorShop or the Resene website for a copy.

In every case it is recommended that the appropriate Data Sheet and Safety Data Sheet are consulted prior to application.

Please ensure that use of this product is compatible with the substrate and surface preparation method and that the colour in this container is the same as selected. When using multiple packs of this product on the same project please mix them together before use. Resene does not accept any responsibility for the application of incorrect product to substrate or the application of incorrect colours. Resene products are designed to be used as a system for optimal results. Substitution may cause substandard results or system failure. For further painting advice and information, call 1800 738 383 (AUST), 0800 737 363 (NZ) or visit the Resene website.



COOLCOLOUR  
BK TONE